



Accurate Indication. Reliable Results™

LA-CO Industries Inc.  
1201 Pratt Boulevard  
Elk Grove Village, IL 60007  
P (847) 956-7600  
F (847) 956-9885  
[www.tempil.com](http://www.tempil.com)

## Product Data: Pyromark<sup>o</sup> 2500 Flat Black

### Silicone High Temperature Resistant Coating

A high temperature resistant silicone coating for use directly over mild steel, stainless steel, aluminum, inconel, aluminized steel, and ceramics. Curing at 480°F is required to obtain solvent, abrasion and heat resistance. Primer not required.

<b>COLOR</b>	Flat black
<b>TEMPERATURE RESISTANCE</b>	Up to 2000°F
<b>GUIDELINES FOR USE</b>	
<b>APPLICATION</b>	May be applied by brush, conventional spray, or high volume low pressure spray when air and surface temperatures are between 50°F and 90°F and no rain is expected. Surfaces must be clean and dry, avoid dew or rain. Recoat within one to two hours or after seven days.
<b>DRYING</b>	Air dry overnight then cure at 480°F for 2 hours. For maximum resistance to heat shock, slowly bring to 1000 ° F over a one hour period.
<b>COVERAGE</b>	400 ft <sup>2</sup> /GL
<b>RECOMMENDED FILM THICKNESS</b>	Dry: 1.0 - 2.0 mils (25-50µm)
<b>THINNER</b>	Xylene
<b>PHYSICAL PROPERTIES</b>	
<b>VOC's (ASTM D 2369-87)</b>	5.2 lb/gal. (624 gram/liter)
<b>WEIGHT PER GALLON</b>	9.6 lbs.
<b>FLASH POINT &amp; Method</b>	88°F (T.C.C.)
<b>WEIGHT % SOLIDS</b>	47.2% Volume Solids: 29.0%
<b>VISCOSITY</b>	1500 Centipoise,#3 @ 10 RPM Brookfield Viscometer
<b>SHELF LIFE</b>	One year from ship date when stored in sealed container below 85°F.

#### Limitation of Liability

This product and information provided is intended for use by persons having skill in industry at their own discretion and risk. Since we have no control over the application or use of this material, we do not provide expressed or implied guarantee or warranty. This product is sold on the condition that each user makes their own evaluation to determine the suitability of the material for their particular use.